

Technical Datasheet

Liquid Coating Resins and Additives

Solvoya® D6098-MS

Edition 04-2020

Solvoya® D6098-MS is a chain stopped short oil air-drying alkyd resin based on Non- yellowing sun flower fatty acids - available in solids of 55.0±1.0% in White spirit & Xylene

Mode of application: Air physical dry, Nitrocellulose and catalyzed drying.

PERFORMANCE & APPLICATIONS

- Chain stopped
- Very good abrasion
- Extremely fast dry with good adhesion to metal
- Compatible with aliphatic hydrocarbon solvents
- Very good yellowing resistance

- Corrosion resistance primers
- White air drying & stoving finishes
- 2K PU for wood finish
- Road Marking paints
- Automotive refinishing enamels

SUPPLY SPECIFICATIONS

- Delivery form
- Dilution form
- Gardner viscosity at 25°C
- Brookfield approx. viscosity at 25°C
- Gardner Color Scale DIN EN ISO 6271-1
- Acid value mg KOH/gm solid
- OH Content (per solid)

- 55.0 ± 1.0%
- 55.0 ± 1.0%
- Approx. Z5 at 55%
- Approx. 9,800 CP at 55%
- 6.0 max.
- 10.0 max.

TYPICAL COMPOSITION

- Phthalic anhydride content
- Type of oil
- Oil Content
- Type of Polyol
- Type of Solvent(s)

- 27%
- Non-yellowing sun flower fatty acids
- 40%
- Mixed polyols
- White spirit & Xylene

SPECIFIC PROPERTIES

 Aliphatic hydrocarbon 	Soluble	Zinc white	Limited compatibility
 Aromatic hydrocarbon 	Soluble	 Red Lead 	Incompatible
 Chlorinated hydrocarbon 	Limited solubility	 Nitrocellulose 	Compatible
 Alcohols 	Insoluble	 Chlorinated rubber 	Limited compatibility
• Esters	Soluble	 Stand oil 	Incompatible
Ketones	Soluble	 Isocyanate 	Limited compatibility
 Glycol-ethers & esters 	Soluble	 Urea/melamine resins 	Limited compatibility

STORAGE

Solvoya® D6098-MS is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

STABILITY

Solvoya® D6098-MS is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

REMARKS

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.