

Solvoya[®] M5213-X

Edition 04-2020

Solvoya[®] M5213-X is a standard medium alkyd resin based on Soya bean oil or Soya Fatty Acid - available in solids of 70 ± 1% in Xylene.

Mode of application: Air physical dry

PERFORMANCE & APPLICATIONS

- Brushability & leveling
- Excellent drying process, toughness & abrasion resistance
- Good wetting properties & yellowing resistance
- Recommended for enamel undercoat, do it yourself paints
- Recommended for structural steel paints
- Quick air drying metal primers and stoving primers

SUPPLY SPECIFICATIONS

• Delivery form	70.0 ± 1%
• Dilution form	70.0 ± 1%
• Acid value mg KOH/gm solid	10.0 max.
• Gardner viscosity at 25°C	Approx. X-Y at 70%
• Brookfield approx. viscosity at 25°C	Approx. 1300 CP at 70%
• Gardner Color Scale DIN EN ISO 6271-1	5.0 max.

TYPICAL COMPOSITION

• Phthalic anhydride content	34%
• Type of oil	Soya bean oil or Soya Fatty Acid
• Oil Content	48%
• Type of Polyol	Glycerin
• Type of Solvent(s)	Xylene

SPECIFIC PROPERTIES

• Aliphatic hydrocarbon	Soluble	• Zinc white	Limited compatibility
• Aromatic hydrocarbon	Soluble	• Red Lead	Limited compatibility
• Chlorinated hydrocarbon	Soluble	• Nitrocellulose	Incompatible
• Alcohols	Insoluble	• Chlorinated rubber	Limited compatibility
• Esters	Soluble	• Stand oil	Incompatible
• Ketones	Soluble	• Isocyanate	Incompatible
• Glycol-ethers & esters	Soluble	• Urea/melamine resins	Limited compatibility

STORAGE

Solvoya[®] M5213-X is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

STABILITY

Solvoya[®] M5213-X is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

REMARKS

- For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).
- The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you to obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.