## Egyptian British Co. Specialty Chemicals & auxiliaries

## **Technical Datasheet**

# Solvoya® N6597-X LS

Liquid Coating Resins and Additives

Edition 04-2020

Solvoya<sup>®</sup> N6597-X LS is a short oil Non-dry alkyd resin based on Coconut oil - available in solids from 60% to 70% ± 2% in Xylene **Mode of application:** Bake, NC and/or catalyzed dry.

#### **PERFORMANCE & APPLICATIONS**

Excellent adhesion and gloss level
Good mechanical performance
Good hardness, adhesion and flexibility
High viscosity level
Used for NC-systems, stoving enamels for furniture and automotive refinishes
Recommended for non-yellowing baking enamels
Suitable for PU-finishes & general purpose stoving enamels

#### SUPPLY SPECIFICATIONS

Delivery form	60.0 ± 2%
Dilution form	60.0 ± 2%
Acid value mg KOH/gm solid	8.0 max.
Gardner viscosity at 25°C	Approx. Z5-Z6 at 60%
<ul> <li>Brookfield approx. viscosity at 25°C</li> </ul>	Approx. 9,700 CP at 60%
<ul> <li>OH-Content (Per solids)</li> </ul>	4.00%
Gardner Color Scale DIN EN ISO 6271-1	3.0 max.

#### **TYPICAL COMPOSITION**

Phthalic anhydride content	44%
• Type of oil	Coconut oil
• Oil Content	35%
Type of Polyol	Mixed polyol
• Type of Solvent(s)	Xylene

#### SPECIFIC PROPERTIES

<ul> <li>Aliphatic hydrocarbon</li> </ul>	Insoluble	Zinc white	Incompatible
<ul> <li>Aromatic hydrocarbon</li> </ul>	Soluble	Red Lead	Incompatible
<ul> <li>Chlorinated hydrocarbon</li> </ul>	Soluble	Nitrocellulose	Compatible
Alcohols	Limited solubility	<ul> <li>Chlorinated rubber</li> </ul>	Incompatible
• Esters	Soluble	Stand oil	Limited compatibility
• Ketones	Soluble	<ul> <li>Isocyanate</li> </ul>	Compatible
<ul> <li>Glycol-ethers &amp; esters</li> </ul>	Soluble	<ul> <li>Urea/melamine resins</li> </ul>	Compatible

### STORAGE

Solvoya® N6597-X LS is stable at temperatures up to 30 °C when packed in original containers, Exposure to sun shine should be avoided.

#### **STABILITY**

Solvoya® N6597-X LS is stable for more than 24 months from the date of production mentioned on the pack of each patch, with reference to the above mentioned storage conditions.

#### REMARKS

• For Ideal Drying time test results, EBCA recommends testing after 48 hours from adding the driers to the paint (min. 24 hours).

• The combinations must be tested for their compatibility

Egyptian British Company maintains Material Safety Data sheets (MSDS) on all of its products. These contain important information that you may need to protect your employees and customers against any known health and safety hazards associated with our products. We recommend you obtain copies of MSDS for our products, from our technical representative, and obtain copies of MSDS from your suppliers of other raw materials used with our products.